

AMENDMENTS TO THE CLAIMS

1. (Currently Amended) An ethylene-based polymer which is an ethylene/C4 to C10 α -olefin copolymer and satisfies the following requirements [k1] to [k3] simultaneously:

[k1] melt flow rate (MFR) under a loading of 2.16 kg at 190°C is in the range of 1.0 to 50 g/10 minutes;

[k2] LNR defined as a scale of neck-in upon film molding is in the range of 0.6 to 1.4; and

[k3] take-up speed at break [DS (m/min)] at 160°C and melt flow rate (MFR) satisfy the following relationship (Eq-1):

$$12 \times \text{MFR}^{0.577} \leq \text{DS} \leq 165 \times \text{MFR}^{0.577} \quad (\text{Eq-1}).$$

2. (Original) The ethylene-based polymer according to claim 1, which simultaneously satisfies the following requirements [m1] to [m3]:

[m1] density [d] is in the range of 890 to 950 kg/m³;

[m2] ratio [MT/ η^* (g/Poise)] of melt tension [MT (g)] at 190°C to shearing viscosity [η^* (Poise)] at 200°C at an angular velocity of 1.0 rad/sec. is in the range of 2.00×10^{-4} to 9.00×10^{-4} ; and

[m3] sum [(A+B) (/1000C)] of the number of methyl branches [A (/1000C)] and the number of ethyl branches [B (/1000C)] per 1000 carbon atoms measured by ¹³C-NMR is 1.4 or less.

3. (Currently Amended) The ethylene-based polymer according to claim 1 or 2, which satisfies at least one of the following requirements [n1] to [n3]:

[n1] ratio (Mz/Mw) of Z-average molecular weight (Mz) to weight-average molecular weight (Mw), measured by GPC, is 10 or more;

[n2] the number of terminal vinyl groups (V) per molecular chain calculated from the number of terminal vinyl groups [v (/1000C)] per 1000 carbon atoms measured by IR and number-average molecular weight (Mn) measured by GPC is not higher than 0.47 per molecular chain; and

[n3] melting-point maximum peak [T_m ($^{\circ}\text{C}$)] in DSC and density (d) satisfy the following relationship (Eq-2):

$$(0.315 \times d) - 200 \leq T_m \leq (0.315 \times d) - 170 \quad (\text{Eq-2}).$$

4. (Currently amended) The ethylene-based polymer according to ~~any one of claims 1 to 3~~, claim 1, which is obtained by polymerization using an olefin polymerization catalyst formed from:


a solid carrier, and

(A) a solid transition metal catalyst component obtained by contacting:

(a) a compound of a transition metal of the group 4 in the periodic table, containing at least one ligand having a cyclopentadienyl skeleton,

(b) an organoaluminum oxy compound, and

(c) a multifunctional organic halide represented by the following general formula (I):



wherein R is a (o + p)-valent group containing at least one halogen atom, o and p each represent a positive integer satisfying the relationship (o + p) \geq 2, Q^1 and Q^2 each represent $-\text{OH}$, $-\text{NH}_2$ or $-\text{NLH}$ whereupon L is an arbitrary group selected from a C1 to C20 hydrocarbon group, a C1 to C20 halogen-containing hydrocarbon group, a silicon-containing group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group and a phosphorus-containing group, and L and R, N and R, or N and N may be bound to each other to form a ring, and if necessary


(d) an organoaluminum compound, and if necessary

(B) an organoaluminum compound.

5. (Original) The ethylene-based polymer according to claim 4, which is obtained by polymerization using a catalyst formed from:



a preliminary polymer having a z-average molecular weight of 6,000,000 or more by GPC and having a die-swell ratio of 1.4 or more, pre-polymerized by ethylene, or ethylene and a C4 to C10 α -olefin, with the solid transition metal catalyst component, wherein 0.01 to 1000 g of the polymer is contained per g of the solid transition metal catalyst component, and if necessary (B) an organoaluminum compound.

6. (Original) The ethylene-based polymer according to claim 4 or 5, wherein the multifunctional organic halide (c) is a compound represented by the following general formula (I):




wherein R is a (o + p)-valent group containing at least one halogen atom, o and p each represent a positive integer satisfying the relationship (o + p) \geq 2, Q¹ and Q² each represent -OH, -NH₂ or -NLH whereupon L is an arbitrary group selected from a C1 to C20 hydrocarbon group, a C1 to C20 halogen-containing hydrocarbon group, a silicon-containing group, an oxygen-containing group, a sulfur-containing group, a nitrogen-containing group and a phosphorus-containing group, and L and R, N and R, or N and N may be bound to each other to form a ring.

7. (Currently amended) The ethylene-based polymer according to ~~any one of claims 4 to 6,~~ claim 4, wherein the compound (a) of a transition metal of the group 4 in the periodic table, containing at least one ligand having a cyclopentadienyl skeleton, is a compound represented by the following general formula (II), (III) or (IV):



wherein R^1 to R^6 are independently selected from a hydrogen atom, a halogen atom, a C1 to C20 alkyl group, a C3 to C20 cycloalkyl group, a C2 to C20 alkenyl group, a C6 to C20 aryl group, and a C7 to C20 arylalkyl group, respectively, and can contain a silicon, halogen or germanium atom, and at least one pair of R^3 and R^4 , R^4 and R^5 , and R^5 and R^6 may be bound to each other to form a ring, R^7 is a divalent group having two ligands, and is a C1 to C20 hydrocarbon group, a C1 to C20 halogen-containing hydrocarbon group, a silicon-containing group or a germanium- or tin-containing group, and two substituent groups on the same carbon, silicon, germanium or tin atom may be bound to each other to form a ring, t^1 and t^2 independently represent a group selected from a hydrogen atom, a halogen atom, a C1 to C20 hydrocarbon group, a C1 to C20 halogen-containing hydrocarbon group, a silicon-containing group, an oxygen-containing group,

a sulfur-containing group, a nitrogen-containing group and a phosphorus-containing group, respectively, and M is a transition metal selected from titanium, zirconium and hafnium,



wherein R^7 , t^1 , t^2 and M each have the same meaning as defined in formula (II), R^8 to R^{19} independently represent a hydrogen atom, a halogen atom, a C1 to C20 alkyl group, a C3 to C20 cycloalkyl group, a C2 to C20 alkenyl group, a C6 to C20 aryl group or a C7 to C20 arylalkyl group, respectively, and can contain a silicon, halogen or germanium atom, and adjacent substituent groups out of R^8 to R^{19} may be bound to each other to form a ring.

8. (Currently amended) A thermoplastic resin composition comprising the ethylene-based polymer according to ~~any one of claims 1 to 7.~~ claim 1.

9. (Currently amended) A molded product obtained from the ethylene-based polymer according to ~~any one of claims 1 to 7.~~ claim 1.

10. (Original) A molded product obtained from the thermoplastic resin composition according to claim 8.

11. (Original) The molded product according to claim 9 or 10, wherein the molded product is a film.